

BODY CAR REPAIR? EASY, LINE 1000!



LINE 1000 IS THE ANSWER

Now, body car repair becomes **even easier** with Line 1000 with **renewed formula**.

Easy, as Line 1000 products are easy to use. **Easy**, as the application of Line 1000 makes work simpler. **Easy**, as the storage management will be more convenient, thanks to the excellent value for money.

Which is the perfect choice for body car shops?

Easy, Line 1000



PAINT AND COATING SOLUTIONS
FOR DECORATIVE, FIRE PROTECTION,
INDUSTRY AND CAR REFINISH
MARKET SECTORS



F 1000

cod. 3130
Universal polyester filler

Highly versatile two-pack plaster in paste, with good flexibility and adhesion on galvanized steel sheet, steel, aluminum, light alloys and fiberglass. Excellent sanding and easy application make F1000 a good basic product to repair every kind of support, both in bodywork and in industrial applications.

Technical features

Colour:	yellow
Gel Time:	4-6 min
Complete polymerization:	2 hours
Sand:	after 30 min
Curing ratio:	1-3% by weight
Hardener:	4000 7333 in paste red

HIGH SPECIFIC WEIGHT

EXCELLENT SANDING



GP 1000

cod. 1549
Two-pack acrylic primer

Primer for spray application having a high solid content, quick drying, good filling power, easy dry and wet sanding, good adhesion to iron surfaces, polyester putting and existing paints.

It is easily sanded, and produces heavy dust, which falls down without floating in the air. Low absorption and good adhesion guarantee smooth, brilliant and firmly adhering enamel films.



Technical features

Colour:	grey
Pot-life:	40 min
Suggested thickness:	80-120 µm dry film
Sand:	after 6 hours
Coverage:	2,5 - 3,5 m ² /l with two coats
Curing ratio:	5: 1 in volume
Hardener:	4537 HARD. SPEEDPRIMER and GP 1000

IMPROVED THIXOTROPY

EVEN FOR HIGH THICKNESSES

NEW FASTER HARDENER

FAST DRYING

GOOD FILLING

LOW ABSORPTION



EASY 1000

cod. 1381
2K anti-scratch acrylic clear coat

New-generation 2K acrylic clear-coat, it is easy to apply and spreads very well. It features high gloss, excellent resistance to scratches (car-wash brushes) and anti-yellowing properties. Quick drying and easy to use, it is perfect for double-layer finishes in car bodywork. 4105 SLOW, 4305 STANDARD, 4505 FAST.



Technical features

Pot-life:	2 hours
Handling:	6 - 8 hours
Polishing:	24 hours
Sheen:	90 - 92 gloss (Gardner 60°)
Suggested thickness:	50 µm dry film
Coverage:	6 - 8 m ² /l with two coats
Curing ratio:	2:1 in volume
Hardener:	4105 SLOW, 4305 STANDARD, 4505 FAST

EVEN MORE GLOSSY

INCREASED TOTAL NON-VOLATILE

EASY TO APPLY

2:1 CURING RATIO

SCRATCH RESISTANT