

Speed Line



2K acrylic clear coat and primer

- Ultra fast drying
- High content of solid substances



**INNOVATING
SURFACES FOR
CAR REFINISH**

2K ACRYLIC CLEAR-COAT UHS ULTRA FAST



Curing ratio: 2:1 in volume
Hardener B: 4376 STANDARD UHS

Two-component acrylic clear-coat, non-yellowing, excellent quality, with a high solid content (VOC content less than 420 g/l) and ultra-fast drying.

- **Ultra-fast drying**
- **Non-yellowing**
- **High content of solid substances**

Technical features

Appearance	brilliant > 95 Gloss 60°
Pot life	30 - 40 min
Dust free	15 min
Handling	1 h
Through drying	3 h
Oven drying	15 min a 60-65°C
Recommended thicknesses	45 - 50 µm dry film

- Dilution max 8% with 1653 DIL PER ACR.
- Cover rate 8 - 9 m²/l with 2 coats

Speedprimer

2K DRYING ACRYLIC PRIMER ULTRA FAST



Curing ratio: 5:1 in volume
Hardener B: 4537 IND PER SPEED PRIMER-GP 1000

Primer applicable by spray, characterized by extremely rapid drying, high content of solid substances, excellent filling properties, good sandability, applicable on steel sheet, polyester putties and old, hardened paints. The very low absorbing power and the excellent adhesion will give as result a final enamel film smooth, bright and firmly adhering to the surface.

- **Ultra-fast drying**
- **High content of solid substances**
- **Excellent filling properties**

Technical features

Pot life	25 min
Touch dry	45 min
Sandable	3 h
Oven drying	10 - 15 min a 60°C
Recommended thicknesses	80 - 120 µm secchi

- Dilution max 10% in weight with 1653 DIL PER ACR., 1648 DIL PER ACR. LENTO
- Cover rate 3 - 4 m²/l with 2 coats



IMPA S.p.A. Unipersonale - Via Crevada, 9/E
31020 San Pietro di Feletto TV - ITALY
T +39 0438 4548
F + 39 0438 454915
info@impa.it - www.impa.it

Company under the management
and coordination of Fassa S.r.l.

AUTHORIZED DEALER