

1359 STAINED WAX

WAX-EFFECT FINISH WITH UV FILTERS



Advantages

- Excellent water repellency
- Wax-effect with UV filters

Description and Use

Wax-effect wood stain resistant to weathering, formulated with specific additives which give optimal water-repellent effect. The film enhances the natural aspect of wood, preserving it from the effect of degrading agents. STAINED WAX is suitable for the maintenance of indoor and outdoor woodwork such as matchboarding, attics, fixtures, fences, balconies and can be applied on new or previously painted surfaces. It can be coloured using the ADVANCE HT tinting system.

Substrate preparation

ON NEW OR HIGHLY ABSORBENT TIMBER:

- Carry out a treatment with SIMPLE WOOD code 1442 and then apply two coats of STAINED WAX, slightly sanding between coats to remove the raised wood fibers.

ALREADY PAINT WOOD:

- The whole surface should be roughened and any flaking parts should be removed, then it is possible to proceed with the application of two coats of STAINED WAX.

Surface must be dry, clean, free from oil or grease.

Application

Application method:

- brush
- spray

Product preparation:

Mix to achieve even colour and consistency.
Dilute with ACQUARAGIA (white spirit) code 1602 at 5-10%.

Recoating:

After 14-16 hours.

Storage life

If stored in a cool, dry place, away from sources of heat and sheltered from sunlight, in its sealed original packaging, the product has a shelf life of 12 months. Check the product's shelf life by referring to the production batch number shown on the packaging. The batch number is made of eight numeric characters in which the first four digits identify the year and month of production. Once the product has expired, it must be disposed of in accordance with the current legislation.

Technical features

Colour	see WOOD SOLUTIONS colour card
Binder	alkyd resin
Appearance of the dry film	semi-matt with wax effect
Specific weight *	0.90 kg/l (±0.02)
Viscosity *	50-70 seconds ISO-DIN Cup 6
Indicative actual yield	5-6 m ² /l per two coats, according to the type of wood, the porosity and the absorption grade
Air drying (20°C - 65% RH)	1 hour. dust-free
	4-5 hours, dry to touch
	24-48 hours, through drying
EU limit values for VOC content (Directive 2004/42/EC)	Cat. A/e. SB: max VOC 400 g/l product VOC < 400 g/l
* May change according to the colour.	
The data are measured at a temperature of 20°C.	

Warnings

- Surface and ambient temperature must be above + 5 (41°F) and below 35°C (95°F).
- Wood must have a maximum humidity of 15%.
- High humidity and excessive thickness can considerably delay the hardening of the applied film.
- Product recommended for expert users.
- It is recommended to acquire all the material required to finish the work of the same batch.
- The information provided on this technical datasheet is based on our technical and practical knowledge and experience. The technical data refer to the average characteristics of the basic product and are determined under controlled laboratory conditions. The variability of the raw materials available on the market and the tinting of the product can lead to slight deviations in the declared values, in the colour and in the aesthetic effects obtained. It is therefore necessary for the purchaser/user to personally verify, before application, the suitability of the product for the intended use, in particular when different batch numbers of the same material are used in the same work/site.

The above mentioned data are meant to facilitate our customers in the use of our products. IMPA is not responsible for applications of products carried out beyond its direct control. For further technical information about specific systems and/or special applications, please contact our TECHNICAL SERVICE at assistenza.technica@impa.it.