

1441 PRATIK WOOD

THIXOTROPIC SOLVENT-BASED WOOD STAIN WITH UV FILTERS



Advantages

- Appearance thixotropic
- With UV filters

Description and Use

PRATIK WOOD is a thixotropic, matt, solvent based wood stain formulated with alkyd resins and UV filters able to protect wood from sunrays and weathering.

It is perfect both as finishing and as brightening on already treated wooden surfaces, both indoors and outdoors, such as fixtures, beams, balconies, doors, windows, etc.

It is available in colourless version or coloured with transparent pigments that make the wood grain visible and highlight. It can be coloured using the ADVANCE HT tinting system.

Substrate preparation

Surface must be dry, clean, free from oil or grease.

To obtain perfect protection it is recommended to recoat PRATIK WOOD 10 hours after application with two coats of FLATTING code 1312.

In case to protect the item with a wood stain only, apply two coats of PRATIK WOOD and repeat the treatment every two years.

Application

Application method:

- brush

Product preparation:

Mix to achieve even colour and consistency.

Ready-to-use.

To reduce the shade intensity, it's possible to mix the coloured versions with colourless PRATIK WOOD.

Storage life

If stored in a cool, dry place, away from sources of heat and sheltered from sunlight, in its sealed original packaging, the product has a shelf life of 24 months. Check the product's shelf life by referring to the production batch number shown on the packaging. The batch number is made of eight numeric characters in which the first four digits identify the year and month of production. Once the product has expired, it must be disposed of in accordance with the current legislation.

Technical features

Colour	see WOOD SOLUTIONS colour card
Appearance after impregnation	matt
Specific weight *	083 kg/l (± 0.02)
Indicative actual yield	9-12 m ² /l per one coat, according to the type of wood, the porosity and the absorption grade.
Air drying (20°C - 65% RH)	10-12 hours
EU limit values for VOC content (Directive 2004/42/EC)	Cat. A/f. SB: max VOC 700 g/l product VOC < 700 g/l
AFNOR NF T 36-005 classification	Family I - Category 4a
* May change according to the colour.	
The data are measured at a temperature of 20°C.	

Warnings

- Surface and ambient temperature must be above + 5 (41°F) and below 35°C (95°F).
- Wood must have a maximum humidity of 15%.
- High ambient humidity and excessive thickness may delay hardening of the applied film.
- Product recommended for expert users.
- It is recommended to acquire all the material required to finish the work of the same batch.
- The information provided on this technical datasheet is based on our technical and practical knowledge and experience. The technical data refer to the average characteristics of the basic product and are determined under controlled laboratory conditions. The variability of the raw materials available on the market and the tinting of the product can lead to slight deviations in the declared values, in the colour and in the aesthetic effects obtained. It is therefore necessary for the purchaser/user to personally verify, before application, the suitability of the product for the intended use, in particular when different batch numbers of the same material are used in the same work/site.

The above mentioned data are meant to facilitate our customers in the use of our products. IMPA is not responsible for applications of products carried out beyond its direct control. For further technical information about specific systems and/or special applications, please contact our TECHNICAL SERVICE at assistenza.technica@impa.it.