

1449 PRATIK WOOD PLUS

WAXED SOLVENT-BASED UV RESISTANT
THIXOTROPIC WOOD STAIN



Advantages

- Appearance thixotropic
- with UV filters and wax

Description and Use

Matt, thixotropic, solvent based wood stain formulated with alkyd resins and UV filters able to protect wood from sunrays and weathering.

The addition of water-repellent additives makes the wood waterproof, avoiding water absorption, but allowing natural transpiration of the living component to keep the wood bright and natural for a long time.

It is particularly suitable for both indoor and outdoor treatment on doors, windows, fixtures, balconies, fences, beams, etc. and on all item, constructions and/or wooden structures exposed to water and sunlight.

It can be coloured using the ADVANCE HT tinting system.

Substrate preparation

Surface must be dry, clean, free from oil or grease.

For optimal protection, it is recommended to recoat PRATIK WOOD PLUS 10 hours after application, after light sanding, with two coats of FLATTING cod. 1312.

In case to protect the item with a wood stain only, apply two coats of PRATIK WOOD PLUS and repeat the treatment every two years.

Application

Application method:

- brush

Product preparation:

Mix to achieve even colour and consistency.

Ready-to-use.

To reduce the shade intensity, it is possible to mix the coloured versions with colourless PRATIK WOOD PLUS.

Storage life

If stored in a cool, dry place, away from sources of heat and sheltered from sunlight, in its sealed original packaging, the product has a shelf life of 24 months. Check the product's shelf life by referring to the production batch number shown on the packaging. The batch number is made of eight numeric characters in which the first four digits identify the year and month of production. Once the product has expired, it must be disposed of in accordance with the current legislation.

Technical features

Colour	transparent
Appearance after impregnation	matt
Specific weight *	083 kg/l (± 0.02)
Indicative actual yield	9-12 m ² /l per one coat, according to the type of wood, the porosity and the absorption grade.
Air drying (20°C - 65% RH)	10-12 hours
EU limit values for VOC content (Directive 2004/42/EC)	Cat. A/f. SB: max VOC 700 g/l product VOC < 700 g/l
* May change according to the colour.	
The data are measured at a temperature of 20°C.	

Warnings

- Surface and ambient temperature must be above + 5 (41°F) and below 35°C (95°F).
- Wood must have a maximum humidity of 15%.
- High humidity and excessive thickness can considerably delay the hardening of the applied film.
- Product recommended for expert users.
- It is recommended to acquire all the material required to finish the work of the same batch.
- The information provided on this technical datasheet is based on our technical and practical knowledge and experience. The technical data refer to the average characteristics of the basic product and are determined under controlled laboratory conditions. The variability of the raw materials available on the market and the tinting of the product can lead to slight deviations in the declared values, in the colour and in the aesthetic effects obtained. It is therefore necessary for the purchaser/user to personally verify, before application, the suitability of the product for the intended use, in particular when different batch numbers of the same material are used in the same work/site.

The above mentioned data are meant to facilitate our customers in the use of our products. IMPA is not responsible for applications of products carried out beyond its direct control. For further technical information about specific systems and/or special applications, please contact our TECHNICAL SERVICE at assistenza.technica@impa.it.