

1539 BUMPER PAINT TX

TEXTURED PAINT FOR BUMPERS AND PLASTIC TRIMS



Advantages

→ Single coat finish

Description and Use

One-component textured varnishing product, fast drying with good adhesion, optimal resistance against weathering and washouts; it has the same semimatt aspect as the original bumpers.

Can be used as a single-coat finishing product. Recoatable.

Excellent adhesion to most plastic surfaces used in car bumpers manufacturing (polypropylene, polycarbonate, ABS, Pohan, xenoy, rigid polyurethane, fiberglass reinforced polyester, etc. except for polyethylene and mixture containing it).

Substrate preparation

Surface to be treated must be dry, clean and free from oil, bitumen and mud stains.

Clean off silicon or polishing wax traces using a wipe soaked with ANTISILICONE code 1618.

Application

Application method:

- air mix spray gun with nozzle Ø 1.6-1.8 mm and pressure of 2.0-2.5 bar.

Product preparation:

Mix to achieve even colour and consistency.

Dilution:

- Add 0 to 10% of DILUENTE PER NITRO ANTINEBBIA (cellulose thinner) code 1616

Storage life

If stored in a cool, dry place, away from sources of heat and sheltered from sunlight, in its sealed original packaging, the product has a shelf life of 24 months. Check the product's shelf life by referring to the production lot shown on the packaging. The lot number comprises of eight numeric characters in which the first four digits identify the year and month of production. Once the product has expired, it must be disposed of in accordance with current legislation.

Technical features

Colour	see price list
Binder	blend of alkyd and acrylic resins
Specific weight	may change according to the colour
Ready-to-use/apply viscosity **	20 - 25 sec. cup FORD 4
Gloss	satın
Recommended thicknesses	50-100 µm dry film. High thickness is not needed
Practical cover rate *	3-5 m ² /l according to the applied thickness
Air drying (20°C - 65% RH) per 80-100 µm thickness	30 minutes, dry to touch
	8 hours, through drying
Recoatible	after 4-6 hours
EU limit value of VOC content (Directive 2004/42/EC)	Category B/e, SB: VOC max 840g/l product VOC < 840g/l
AFNOR NF T 36-005 classification	Family I - Category 4a/7b1
* The cover rate is calculated on the suggested thickness and applied on plane and regular surfaces.	
** May change according to the colour.	
The data are measured at a temperature of 20°C.	

Warnings

- For professional use only.
- Always read the safety datasheet before use.
- Dispose of contents / container in accordance with national regulations.
- It is recommended to acquire all the material required to finish the work of the same batch.
- The information provided on this technical datasheet is based on our technical and practical knowledge and experience. The technical data refer to the average characteristics of the basic product and are determined under controlled laboratory conditions. The variability of the raw materials available on the market can lead to slight deviations in the declared values. It is therefore necessary for the purchaser/user to personally verify, before application, the suitability of the product for the intended use, in particular when different batch numbers of the same material are used in the same work/site.

The above mentioned data are meant to facilitate our customers in the use of our products. IMPA is not responsible for applications of products carried out beyond its direct control. For further technical information about specific systems and/or special applications, please contact our TECHNICAL SERVICE at assistenza.technica@impa.it.