

1821 CLOROCAUCCIÙ MODIFICATO

MODIFIED CHLORINATED RUBBER ENAMEL



Description and Use

Gloss finishing coat based on chlorinated rubber resins modified with alkyd resins, featuring good flexibility and resistance to water and bumps.

Suitable to protect agricultural machinery, structural steel and work and ferrous metal structures exposed in industrial and marine environments.

It can be coloured using the ADVANCE HT tinting system.

Substrate preparation

IRON SURFACES:

- Take off any trace of rust, iron scale, grease and moisture by sand-blasting SA2.5 grade; otherwise, carry out a careful mechanical cleaning followed by solvent degreasing.
- Apply a first coat of primer FONDO R.E. code 1827 or CONIT code 1014.

Application

Application method:

- air mix spray gun with nozzle Ø 1.5-1.8 mm and pressure of 3-4 bar.
- airless
- brush: only for small surfaces

Product preparation:

Stir thoroughly the product to achieve even colour and consistency.

Dilute with DILUENTE PER CLOROGOMMA cod. 1609 or DILUENTE PER NITRO ANTINEBBIA cod. 1616 at 20-30%.

Recommended thicknesses:

40-50 µm dry film, waiting 5-10 minutes between coats.

Storage life

If stored in a cool, dry place, away from sources of heat and sheltered from sunlight, in its sealed original packaging, the product has a shelf life of 12 months. Check the product's shelf life by referring to the production lot shown on the packaging. The lot number comprises of eight numeric characters in which the first four digits identify the year and month of production. Once the product has expired, it must be disposed of in accordance with current legislation.

Technical features

Color	see price list
Appearance of the dry film	glossy
Viscosity **	1500-2500 mPa.s Brookfield rpm 20 s 4
Practical cover rate *	7-8 m ² /kg (2 layers)
Air drying	20-30 minutes, dust free
	3-4 hours, dry to touch
	24 hours, through drying
AFNOR NF T 36-005 classification	Family I - Category 8a/4a
* The cover rate is calculated on the suggested thickness and applied on plane and regular surfaces.	
** May change according to the colour.	
The data are measured at a temperature of 20°C and 65% R.H.	

Warnings

- For industrial use only.
- Exclusively for use not restricted from Directive 2004/42/EC.
- Always read the safety datasheet before use.
- Dispose of contents / container in accordance with national regulations.
- It is recommended to acquire all the material required to finish the work of the same batch.
- The information provided on this technical datasheet is based on our technical and practical knowledge and experience. The technical data refer to the average characteristics of the basic product and are determined under controlled laboratory conditions. The variability of the raw materials available on the market and the tinting of the product can lead to slight deviations in the declared values, in the colour and in the aesthetic effects obtained. It is therefore necessary for the purchaser/user to personally verify, before application, the suitability of the product for the intended use, in particular when different batch numbers of the same material are used in the same work/site.

High environment humidity and excessive thickness may retard the hardening of the applied film.

The above mentioned data are meant to facilitate our customers in the use of our products. IMPA is not responsible for applications of products carried out beyond its direct control. For further technical information about specific systems and/or special applications, please contact our TECHNICAL SERVICE at assistenza.technica@impa.it.