

3559 CANOVA VERTICALE TRASPARENTE

TRANSPARENT THIXOTROPIC EPOXY MASTIC



Building



Two-component



Ready-to-use



By spatula



Dry sandable

Description and Use

Two-component mastic, for application to vertical surfaces, featuring strong adhesion properties and good weathering resistance.

Especially suitable for outdoor work on granite, marble and stone.

Substrate preparation

Surfaces to be treated must be dry, clean, dust free, without grease or wax traces.

Application

Application method:

- trowel

Product preparation:

The product is ready to use.

Application method:

stir thoroughly the two components, according to the recommended ratio; catalyse limited quantities of product, in order to avoid a quick reaction ("mass effect").

It is suggested 200-250 gr for each catalysis.

The complete hardening and the maximum chemical resistance will be reached after 7 days.

Storage life

24 months in its original packing

Technical features

Color	semi-transparent
Type of product	two component
Hardener	CANOVA VERTICALE TRASPARENTE B code 4559
Binder	epoxy-polyamine
Specific gravity comp. A	1.17 kg/l ($\pm 0,02$)
Specific gravity comp. B	1.10 kg/l ($\pm 0,02$)
Curing ratio	2:1 weight of A /weight of B
Gel time	20-30 minutes
Sandable	after 5 hours
The data are measured at a temperature of 20°C and 65% R.H.	

Warnings

- For professional use only.
 - Always read the safety datasheet before use.
 - Dispose of contents / container in accordance with national regulations.
 - It is recommended to acquire all the material required to finish the job from the same batch.
 - The information provided on this technical datasheet is based on our technical and practical knowledge and experience. The technical data refer to the average characteristics of the basic product and are determined under controlled laboratory conditions. The variability of the raw materials available on the market can lead to slight deviations in the declared values. It is therefore necessary for the purchaser/user to personally verify, before application, the suitability of the product for the intended use, in particular when different lots of the same material are used in the same job/site.
- It is recommended not to use when the temperature is below + 10°C (50°F) or the relative humidity exceeds 80%, because the reaction becomes too slow.**

The above mentioned data are meant to facilitate our customers in the use of our products. IMPA is not responsible for applications of products carried out beyond its direct control. For further technical information about specific systems and/or special applications, please contact our TECHNICAL SERVICE at assistenza.technica@impa.it.