



0003 POLY VA

VINYL FIXATIVE-BONDING FOR WALLS



Advantages

- High yield
- Primer suitable for encapsulation cycles

Description and Use

POLY VA is a fixative-insulating agent for interior use, vinyl-based, offering high resistance to alkali, suggested to avoid the absorbing differences on the plasterworks, and to ensure a perfect paint adhesion.

POLY VA can be used as a TYPE D coating to encapsulate cement-asbestos surfaces, in order to prevent fibers dispersion during removal or disposal works (as provided for by Ministerial Decree dated 20 August 1999 reported in the 22/10/1999 issue of the Official Gazette).

Substrate preparation

- On old or chalking surfaces brush and scrape taking off the flaking parts, fill up with putty and then apply the bonding POLY VA.

TYPE D coating:

- Using POLY VA as a TYPE D coating to be applied on cement-asbestos surfaces, the fixative has to be stained with 1 - 2% of PASTA ROSSO OSSIDO code 09207330 in order to ensure, once applied, a layer of colour contrasting with the substrate.
- POLY VA so coloured must be thinned 1:3 with water and directly applied avoiding the cleaning of the surface.

Application

Application method:

- brush
- roller
- spray

When POLY VA is used as a TYPE D coating, only spray application is permitted.

Dilution:

- used as fixative-bonding: 1 part of POLY VA + 7 parts of water
- used as TYPE D coating: 1 part of POLY VA + 3 parts of water

Storage life

PROTECT FROM FROST. Store the packaged product at a temperature between +5°C and +35°C.

If stored in a cool, dry place, away from sources of heat and sheltered from sunlight, in its sealed original packaging, the product has a shelf life of 12 months. Check the product's shelf life by referring to the production batch number shown on the packaging. The batch number is made of eight numeric characters in which the first four digits identify the year and month of production. Once the product has expired, it must be disposed of in accordance with current legislation.

Technical features

Colour	milky-transparent
Specific weight	1.02 kg/l (± 0.02)
Practical cover rate *	50-60 m ² /l related to the dilution ratio of 1:7
Practical cover rate when used as a TYPE D coating	8-10 m ² /l referred to 8-9 µm dry film according to surface absorption.
Recoatible	after 2-3 hours
Air drying at 20°C 65% RH as TYPE D coating	4-5 hours
EU limit value of VOC content (Directive 2004/42/EC)	Category A/h, WB: VOC maximum 30 g/l product VOC < 30 g/l
* The yield may vary according to the roughness and absorption of the substrate and in relation to the application system used.	
The data are measured at a temperature of 20°C.	

Warnings

- Product recommended for professional use.
- Always refer to the safety data sheet for the relevant products.
- Solvents or thinners used for cleaning tools, as well as any product residues, must not be released into the environment or poured down domestic drains. The recipient/product/thinner or cleaning solvent must be disposed of in accordance with national regulations.
- Surface and ambient temperature must be above + 5 (41°F) and below 35°C (95°F).
- It is recommended to acquire all the material required to finish the work of the same batch.
- The information provided on this technical datasheet is based on our technical and practical knowledge and experience. The technical data refer to the average characteristics of the basic product and are determined under controlled laboratory conditions. The variability of the raw materials available on the market can lead to slight deviations in the declared values. It is therefore necessary for the purchaser/user to personally verify, before application, the suitability of the product for the intended use, in particular when different batch numbers of the same material are used in the same work/site.

NOTE: Do not apply in foggy or rainy weather, or when the relative humidity exceeds 75%.

The above mentioned data are meant to facilitate our customers in the use of our products. IMPA is not responsible for applications of products carried out beyond its direct control. For further technical information about specific systems and/or special applications, please contact our TECHNICAL SERVICE at assistenza.technica@impa.it.