

3130 F 1000

UNIVERSAL POLYESTER FILLER



Car refinish



Industry



Two-component



Ready-to-use



By spatula



Dry sandable

Advantages

→ Excellent sanding

Description and Use

Bi-component plaster in paste with good flexibility and high adhesion onto galvanized sheet steel, steel, aluminum, light alloys and fiberglass.

The excellent sanding and easiness to apply make it an excellent base product for repair-work, filling and shearing on every type of support-structure, both in bodywork and in industrial activities.

Substrate preparation

Surfaces to be filled must be dry, clean, free of dust or grease and made rough by sanding.

Suitable substrates:

Steel, cast iron, aluminium, light alloys, zinc plated steel, aged car paints and fiberglass free of detaching agents. For further information apply to our TECHNICAL SERVICE.

Not suitable substrates:

Wash primer, epoxy primers with phenolic hardeners, thermoplastic varnishes, solvent sensitive primers.

Application

Application method:

- By spatula

Product preparation:

To use the filler, add the hardener according to the room temperature and the requested gel time, like the following schedule:

Curing ratio	Tube
Temperature up to 10°C (50°F)	3 to 100 by weight
Temperature between 10 and 20°C (50 ÷ 68°F)	2 to 100 by weight
Temperature up to 20°C (50°F)	1 to 100 by weight

Application method:

Stir thoroughly the two components and apply making a light pressure on the spatula, to get a better adhesion.

For the sanding work it's suggested the use of sandpaper P80, P120, P180, P240 grit.

For best final result, before applying the top-coat spray over the filler a coat of the High Solids Primer EQUALIX HS code 1513 or STAR PRIME HT code 1543.

Infrared rays lamps

Using medium or short waves IR lamps, waiting time before sanding can be reduced, getting at the same time a drier surface.

After application allow some minutes before radiating the filler.

It is important that filler temperature never exceeds 90°C (194°F).

Refer to the lighting system manufacturer to get correct user information (e.g. times and distances).

Storage life

If stored in a cool, dry place, away from sources of heat and sheltered from sunlight, in its sealed original packaging, the product has a shelf life of 12 months. Check the product's shelf life by referring to the production batch number shown on the packaging. The batch number is made of eight numeric characters in which the first four digits identify the year and month of production. Once the product has expired, it must be disposed of in accordance with the current legislation.

Technical features

Colour	yellow
Specific gravity comp. A	1.82 kg/l (± 0.03)
Hardener	paste code 4000
Curing ratio	100 of A + 1-3 of B by weight
Gel time	4-6 minutes with 2 parts by weight of hardener to 100 parts of A
Complete polymerisation	after 2 hours
Sanding	after 30 minutes on medium thickness
AFNOR NF T 36-005 classification	Family 4 - Class 3
EU limit value of VOC content (Directive 2004/42/EC)	Category B/b, SB: VOC max 250g/l; product VOC < 250g/l
The data are measured at a temperature of 20°C and 65% R.H.	

Warnings

- For professional use only.
- Always read the safety datasheet before use.
- Solvents or thinners used for cleaning tools, as well as any product residues, must not be released into the environment or poured down domestic drains. The recipient/product/thinner or cleaning solvent must be disposed of in accordance with national regulations.
- Clean equipment immediately after use with cellulose thinner.
- It is recommended to acquire all the material required to finish the work of the same batch.
- The information provided on this technical datasheet is based on our technical and practical knowledge and experience. The technical data refer to the average characteristics of the basic product and are determined under controlled laboratory conditions. The variability of the raw materials available on the market can lead to slight deviations in the declared values. It is therefore necessary for the purchaser/user to personally verify, before application, the suitability of the product for the intended use, in particular when different batch numbers of the same material are used in the same work/site.

Avoid to apply when temperature is below + 10°C (50°F)

The above mentioned data are meant to facilitate our customers in the use of our products. IMPA is not responsible for applications of products carried out beyond its direct control. For further technical information about specific systems and/or special applications, please contact our TECHNICAL SERVICE at assistenza.technica@impa.it.