Speed Line

2K acrylic clear coat and primer

→ Ultra fast drying
→ High content of solid substances



IMPA CONTEMPORARY IDEAS

INNOVATING
SURFACES FOR
CAR REFINISH

Speedlak UHS

1389

90006174 - 12/25

ULTRA FAST CLEARCOAT UHS

Two-component acrylic clear-coat, non-yellowing, excellent quality, with a high solid content (VOC content less than 420 g/l) and ultra-fast drying.



- → **Ultra-fast drying**
- → **Non-yellowing**
- → **High content of solid substances**

Technical features

Appearance	brilliant > 95 Gloss 60°
Pot life	30 - 40 min
Dust free	15 min
Handling	1 h
Through drying	3 h
Oven drying	not needed/not recommended
Recommended thicknesses	45 - 50 µm dry film
→ Dilution	max 5% with 1653 DIL PER ACR.
→ Cover rate	8 - 9 m²/l with 2 coats

Curing ratio: 2:1 in volume
Hardener B: 4376 STANDARD UHS

Speedprimer

1589

2K ULTRA FAST DRYING ACRYLIC PRIMER

Primer applicable by spray, characterized by extremely rapid drying, high content of solid substances, excellent filling properties, good sandability, applicable on steel sheet, polyester putties and old, hardened paints. The very low absorbing power and the excellent adhesion will give as result a final enamel film smooth, bright and firmly adhering to the surface.



- → **Ultra-fast drying**
- → **High content of solid substances**
- → **Excellent filling properties**

Technical features

Pot life	25 min
Touch dry	45 min
Sandable	3 h
Oven drying	10 - 15 min a 60°C
Recommended thicknesses	80 - 120 µm secchi
→ Dilution	5-10% with 1653 DIL PER ACR.
→ Cover rate	3 - 4 m²/l with 2 coats

Curing ratio: 5:1 in volume
Hardener B: 4537 IND PER SPEED PRIMER

AUTHORIZED DEALER

IMPA S.p.A. Unipersonale – Via Crevada, 9/E
31020 San Pietro di Feletto TV – ITALY
T +39 0438 4548
info@impa.it – www.impa.it
Company under the management
and coordination of Fassa S.r.l.